

SMI, Inc.

12219 SW 131 Avenue
Miami, Florida 33186-6401 USA

Phone: (305) 971-7047
Fax: (305) 971-7048

Attn: Carol Chapin
Simple Green
15922 Pacific Coast Highway
Huntington Harbour, CA 92649

Date: 13-Sep-2005

SMI/REF: 05AUG784

Product: **Extreme Simple Green** (received 08-Aug-2005)
Dilution: (1:13) 7.14%


Partial testing in accordance with:
AMS 1526B
Cleaner for Aircraft Exterior Surfaces
Water-Miscible, Pressure-Spraying Type

3.2.1.2 Total Immersion Corrosion: The product shall neither show evidence of corrosion of the panels nor cause a weight change of any test panel greater than the following, determined in accordance with ASTM F 483:

PANEL	Allowable Weight Change mg/cm ² /24hrs	RESULTS
		DILUTE 1:13 (7.14%)
AMS 4037 anodized per AMS 2470	0.3	0.01
AMS 4041 Aluminum Alloy	0.3	0.01
AMS 4049 Aluminum Alloy	0.3	0.01
AMS 4376 Mg dichromated AMS 2475	0.2	0.02
AMS 4911 Titanium Alloy	0.1	0.01
AMS 5045 Carbon Steel	0.8	0.01

Result Conforms

Respectfully submitted,



Patricia D. Viani, SMI Inc.